


Pharma Solutions

POLYOX™

Resins that allow distinctive drug delivery solutions



What is it?

POLYOX™ resins are nonionic poly (ethylene oxide) polymers. They are white to off-white, free-flowing hydrophilic powders supplied in a wide variety of viscosity grades corresponding to molecular weight, ranging from approximate 100,000 to 7,000,000 daltons. POLYOX™ polymers possess thermoplastic properties, are fast-hydrating and very quickly form hydrogels. They are essentially tasteless, colorless, nonionic and non-caloric. Their unusual combination of properties makes them useful in a surprisingly broad array of pharmaceutical formulations such as controlled release formulations, tablet binding and mucosal bioadhesives.

What is it used for?

Examples:

Application	Recommended POLYOX™ Grades	Benefits & Features
Osmotic Pump Technology	N10, N80, WSR Coagulant, WSR-301, WSR-303	Zero-order release, clinical robustness and little to no food effect
CR Matrix Tablets	WSR Coagulant, WSR-303	Rapid hydrogel formation, excellent tablet binding and lubrication properties
Abuse Deterrence	WSR N12K, N60K, WSR-301, WSR Coagulant, WSR-303	Thermoplasticity and gelling behavior help harden tablets and increase the viscosity of liquid to prevent drug injection
Mucoadhesive Delivery Systems	WSR-301, WSR Coagulant, WSR-303	Adheres well to mucosal membranes
Hot-Melt Extrusion	WSR-N750, WSR-N12K, WSR-301	Highly thermoplastic in nature, POLYOX™ polymers extrude very well

Key Benefits

- High solubility in water and polar solvents
- Very fast hydration, rapid swelling and hydrogel formation
- Molecular weights ranging from 100,000 to 7,000,000 daltons
- Hydrogen bonding functionality and good biocompatibility
- Thermoplastic polymer with low melting point of ~ 65°C
- Does not show a strong pH response due to their nonionic nature
- Tasteless, colorless, nonionic and non-caloric

The information provided herein is based on data IFF believes, to the best of its knowledge, reliable and applies only to the specific material designated herein as sold by IFF. The information contained herein does not apply to use of the material designated herein in any process or in combination with any other material and is provided at the request of and without charge to our customers. Accordingly, IFF cannot guarantee or warrant such information and assumes no liability for its use. Other than as may be expressly set forth in a contract of sale, IFF makes no warranty, express or implied, as to the material set forth herein, including the warranty of merchantability or fitness for a particular use. ©2023 International Flavors & Fragrances Inc. (IFF). IFF, the IFF Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by IFF or affiliates of IFF unless otherwise noted. All rights reserved.



Where science
& creativity meet